### **Continental Petroleums Ltd.**

email: conpetco@gmail.com

\_\_\_\_\_\_

## **CONTOL Lithium Grease AP-3 (Typical Product Data Sheet)**

Contol Lithium Grease AP-3 is a high performance lithium grease formulated with highly refined petroleum oil and fortified with performance additives to give longer life and corrosion protection.

#### **Features and Benefits**

Contol Lithium Grease AP-3 has key benefits as follows:

- Meets NLGI Grade 3 requirements.
- Excellent thermal and oxidation stability.
- Superior protection against rust and corrosion.
- Good resistance to water washout.
- Extended bearing life.
- Recommended operating temperatures between -10 Deg.C and +130 Deg.C.

#### **Applications**

Recommend for antifriction and plain bearings in industrial & automotive applications. They are widely used in steel plants, cement plants and other industrial applications.

Recommend for plain and anti-friction bearings in a vide variety of applications such as automotive, earth moving equipments, gear couplings, electric motors, mining equipments

#### **Specifications**

Contol Lithium Grease AP-3 is recommended for use in applications requiring:

NLGI Grade 3

Meets IS:7623-1993 (Second Rev.) Reaffirmed 2001.

Cont. in Page 2

# **Continental Petroleums Ltd.**

email: conpetco@gmail.com

\_\_\_\_\_

--2--

## **Typical Properties**

CHARACTERISTICS	Lithium GREASE AP-3	METHODS
NLGI Grade	3	<b>ASTM D217</b>
Thickener Type	Li-Complex	
Color	Light Yellow	Visual
Texture	Smooth homogeneous	
Dropping Point, °C	198	ASTM D566
Worked Penetration @25Deg C		
After 60 strokes	220-250	
Base Oil Viscosity, cSt		ASTM D445
100°C	15.6	
40°C	150	
Copper Strip Corrosion, rating	<b>1</b> b	<b>ASTM D4048</b>
Leakage Tendency Leakage, grams	2.0	<b>ASTM D1263</b>
Water Resistance at 80°C, % removed	3.9	<b>ASTM D1264</b>
Oil Separation, % loss	1.8	<b>ASTM D1742</b>

The figures quoted are typical, do not constitute a specification and are subject to the usual manufacturing tolerances.